

FABRAL COLOR	SR	IE	SRI	STEEL			ALUMINUM			
				24GA.†	22GA.†	18GA.†	.032"†	.040"†	.050"†	.063"†
Regal White	.68	.86	82	●■▲◆	●	●	●■			●
Bone White	.72	.84	87	●	●	●	●	●	●	
Almond	.63	.86	75	●			●	●		
Sandstone	.54	.86	63	●■▲◆	●		●	●	●	
Surrey Beige	.40	.86	43	●◆	●		●	●	●	
Sierra Tan	.35	.86	37	●			●	●		
Medium Bronze	.30	.87	31	●■◆	●	●	●	●	●	●
Mansard Brown	.29	.86	29	●			●	●	●	
Dark Bronze	.26	.84	24	●■▲◆	●	●	●■	●	●	●
Matte Black	.27	.86	26	●	●		●	●		
Stone Gray	.36	.84	37	●			●			
Slate Gray	.37	.86	39	●◆			●	●		
Charcoal	.32	.85	32	●	●		●	●		
Slate Blue	.26	.85	24	●			●			
Regal Blue	.28	.86	27	●			●			
Patina Green	.29	.87	29	●			●			
Classic Green	.26	.84	24	●■	●		●	●		
Hartford Green	.10	.82	2	●			●			
Brandywine	.26	.85	24	●			●			
Colonial Red	.34	.86	35	●			●			
Pewter	.36	.85	38	●			●			
Bright Silver	.60	.77	68	●			●■			
Silversmith	.53	.78	59	●			●			
Champagne	.37	.83	38	●			●			
Bright Copper	.49	.85	55	●■			●■			

PAINT PERFORMANCE PROPERTIES	HOT DIPPED GALVANIZED STEEL OR GALVALUME®	ALUMINUM
Accelerated Weathering ASTM D 4587 (Drew Cycle Weatherometer) ASTM G 23	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max
Salt Spray ASTM B 117	Hours: 1,000 Total Scribe: Rating 7 1/16" (1.6mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
Humidity ASTM D 2247	Hours: 2,000 Total Rating: 10, no blisters	Hours: 3,000 Total Rating: 10, no blisters
Formability ASTM D 4145	0T-3T	0T-3T
ASTM D 522 (Elongation over 1/2" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
Pencil Hardness ASTM D 3363	HB-2H	HB-2H
Abrasion Resistance ASTM D 968	55-75 Liters of falling sand	55-75 Liters of falling sand
Specular Gloss ASTM D 523	20-35 at 60°	20-35 at 60°
Reverse Impact ASTM D 2794	2 x Metal thickness in inch-lbs. No loss of adhesion	1 1/2 x Metal thickness in inch-lbs. No loss of adhesion
Flame Test ASTM E 84	Class A rated coating	Class A rated coating

- † Standard Coil Width is 48.25"
‡ Standard Coil Width is 44.375"
● Available in Standard Coil Width.
■ Available in 40.25" Coil Width.
▲ Available in 38" Coil Width.
◆ Available in 44.375" Coil Width.

Notes on availability:

- 24ga, .032", .040", .050" & .063" are standard 48.25" in width, 22ga & 18ga are 44.375" in width for painted items.
- Standard inventory is non-embossed. Please contact us for the availability of stucco embossing.
- Protective strippable film is available upon request.
- Metallic/Mica colors are subject to premium pricing.
- Subject to change without notice.
- Unpainted, acrylic coated, Aluminum-Zinc Alloy steel (AZ-55) is maintained in: 26ga x 20", 26ga x 28", 26ga x 48.25", 24ga x 20", 24ga x 24", 24ga x 28", 24ga x 48.25", 22ga x 44.375", 22ga x 48.25", 20ga x 44.375" and 18ga x 44.375".
- All colors are supplied in Medium Gloss (20-35 at 60°). Low Gloss available subject to minimum coating run.

Fabra's standard architectural colors and finishes feature 70% polyvinylidene fluoride (PVDF) resin paint systems to ensure long term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set up charges may apply. Consult www.fabrai.com for additional information.

Kynar®